



887 Kensington Ave. Buffalo, NY 14215

<u>Pad Construction</u>		<u>Description</u>		
Construction				
	Substrate 1	12# Tissue		
	Absorbent	SAP		
	Substrate 2	12# Tissue		
<u>Description</u>		<u>STANDARD DATA</u>		<u>METRIC DATA</u>
Basis WT:		8.1	g/sq.ft.	87 g/sq.m
SAP WT:		4.8	g/sq.ft.	52 g/sq.m.
Thickness		14.5	mils	368 microns
ABSORBENCY IN 0.9% NaCl				
30 SEC:		170	g/sq.ft.	1830 g/sq.m.
5 MIN:		295	g/sq.ft.	3170 g/sq.m.
		36.4	g/g	36.4 g/g
ABSORBENCY IN DI water				
30 SEC:		741	g/sq.ft.	7976 g/sq.m.
5 MIN:		1874	g/sq.ft.	20172 g/sq.m.
		231.4	g/g	231.4 g/g
MD Tensile:		2.2	lb/in.	1.0 kg/in.
MD Elongation:		13.0	%	13.0 %
Yield:		6.2	sq.yd/lb	11.4 sq.m./kg

DATE: 6/04-72

NOTE: THIS TYPICAL DATA IS ONLY AN APPROXIMATION OF THE TRUE VALUES AND IS NOT TO BE USED FOR SPECIFICATION PURPOSES.